

# ABSO-PRO<sup>®</sup> L16

Calcined Attapulgite LVM 16/60

## General description

A premium, all-purpose absorbent with hard, non-slaking granules, made from calcined attapulgite clay.

## Functional use

Dust-free, slip-resistant and non-flammable qualities suit intensive applications for routine or emergency use in the workplace.

## General characteristics

- Inert Mineral Absorbent
- Non-Combustible, Non-Flammable
- Lightweight
- Free Flowing
- High Surface Area
- High Oil Absorption
- High Water Absorption
- Hard, Moisture Resistant Granules
- Non-Swelling
- Low Dust Content

## Technical data

Material Type: Calcined Attapulgite

Appearance: Beige Granules

	TYPICAL	SPECIFICATION
Moisture Content (105° C)*, %:	2	4 max
Water Absorption (Westinghouse Method), %:	135	
Oil Absorption (Westinghouse Method), %:	100	
Granulometry: 16/60 (0.250 – 1.18 mm)		
Sieve Analysis:		
Percent Plus 16 Mesh ( + 1.18 mm):	3	8 max
Percent Minus 60 Mesh (- 0.250 mm):	3	8 max
Apparent Bulk Density, g/cm <sup>3</sup> :	0.57	
pH (5% Suspension):	8	

\*measured 2 hours after production

No warranty of any kind, express or implied, is made with respect to the product described or the data and information contained herein, which are presented in good faith for guidance only. Geohellas recommends that application tests be conducted on products to verify suitability and performance levels.